



Asphalt Refining & Technology Company

Roofing Asphalt

ASTM D - 312 - 00 Specifications

	Softening Pt	Penetration	Ductility	Solubility	Flash
	min / max	77°F	77°F, cm		min
Type III	185-205	15-35	2.5 min	99%	SOOT
Type IV	210-225	12-25	1.5 min	99%	500°F

Typical ARTC Specifications

	Softening Pt	Penetration	Ductility	Solubility	Flash
	min / max	77°F	77°F, cm		min
Type III	195-205	15-35	2.5 min	99%	550
Type IV	210-225	12-25	1.5 min	99%	550

BURA should be applied to normal industry standards. Application temperature is important and should be applied at the Equal Viscous Temperature (EVT) plus or minus 25°F.

Solubility is run in Trichloroethylene.

Flash points are COC (Cleveland Open Cup).